

# Cold Rolled CR Vitreous Enamelling V CV2S1 steel

Revision 6, November 2003

This literature supersedes all previous issues

## GENERAL DESCRIPTION

CV2S1 cold rolled and skin-passed commercial drawing steel guaranteed for general purpose vitreous enamelling with appropriate enamelling practices. Unsuitable for direct-on cover coat or two coat/one fire white enamels.

## TYPICAL USES

Stove liners, heaters.

## AUSTRALIAN STANDARD

AS/NZS 1365

## GUARANTEED PROPERTIES OF STEEL BASE

MECHANICAL PROPERTIES	GUARANTEED %
Transverse tensile	–
Yield strength, MPa	–
Tensile strength, MPa	–
Elong on 80 mm, %	33 min
Hardness, HRB	55 max
HR30T	–
180° transverse bend(L axis)	0t
Uniform elong, %	–
Plastic strain ratio	–
r0	–
r90	–
r45	–

CHEMICAL PROPERTIES	TYPICAL %
Carbon (C)	0.04 - 0.07
Phosphorus (P)	0.005 - 0.020
Manganese (Mn)	0.18 - 0.23
Silicon (Si)	0.005 - 0.010
Sulphur (S)	0.008 - 0.020
Aluminium (Al)	0.03 - 0.05
Nitrogen (N)	0.001 - 0.007

## DIMENSIONAL CAPABILITIES

Preferred thickness mm	Width range mm		Sheet length mm
	Strip	Sheet	
0.50, 0.55	890 - 1220	300 - 1220	1220 - 4880
0.60	890 - 1650	300 - 1650	1085 - 4880
0.65	890 - 1700	300 - 1700	1085 - 4880
0.70	890 - 1750	300 - 1750	1085 - 4880
0.75	890 - 1800	300 - 1800	1085 - 4880
0.80, 0.85, 0.90, 0.95, 1.0, 1.1, 1.2, 1.3, 1.4, 1.5, 1.6, 1.7, 1.8, 1.9	890 - 1810	300 - 1810	1085 - 4880
2.0, 2.2, 2.5, 2.8, 3.0, 3.2	890 - 1320	300 - 1320	1220 - 4870

NOTE: Where maximum widths are less than 1200 mm, any width between half maximum and 610 mm is available by negotiation only. Availability applies only to product supplied direct from Western Port and may change if supplied from BlueScope Steel Service Centres. Slitting and shearing available on request from BlueScope Steel sales offices.

**These dimensions are a reflection of technical capability to produce. Supply conditions may be subject to dimensional restrictions and is subject to BlueScope Steel Sales and Marketing confirmation.**

## NORMAL/OPTIONAL SUPPLY CONDITIONS

	Normal	Optional <sup>#</sup>
Surface finish	Matt	–
Tolerance class		
Thickness	AT	BT
Width	AW	BW
Length	AL	BL
Flatness	AF	BF(Sheet only)
Oiling	Oiled	Not Oiled
Branding	Not Branded	–
Edge Condition	Mill Edge	Trimmed Edge

<sup>#</sup>Optional supply conditions may be subject to dimensional restrictions.

## FABRICATING PERFORMANCE

Method	Rating
Bending	5
Drawing	3
Pressing	3
Roll-forming	5
Welding	5
Painting (pretreatment)	5

where 1 = limited to 5 = excellent, or  
NR = not recommended

Note: It is recommended that customers use product promptly to avoid the possibility of rusting during storage. Oiling improves corrosion resistance but oiled product should be used within three months.

BlueScope is a trade mark of BlueScope Steel Limited.

**Please ensure you have the current data sheet for this product as displayed at [www.bluescopesteel.com.au](http://www.bluescopesteel.com.au)**

## BlueScope Steel Limited

BlueScope Steel Limited ABN 16 000 011 058  
BlueScope Steel (AIS) Pty Ltd ABN 19 000 019 625

Copyright © 2003 BlueScope Steel Limited

**SYDNEY:** (02) 9795 6700 **MELBOURNE:** (03) 9586 2222 **BRISBANE:** (07) 3845 9300 **ADELAIDE:** (08) 8243 7333 **PERTH:** (09) 9330 0666

Produced by Artimprint (02) 9984 8586



# Cold Rolled CR Vitreous Enamelling V CV2S1 steel

Revision 6, November 2003

This literature supersedes all previous issues **Continued**

## TYPICAL PROPERTY RANGES (FOR NORMAL SUPPLY PRODUCT)

Thickness mm	Yield Strength & Tensile Strength MPa																				
	150	160	170	180	190	200	210	220	230	240	250	260	270	280	290	300	310	320	330	340	
0.50 - 0.79																					
0.80 - 1.20																					
1.21 - 3.20																					

**Key**  proof stress  tensile strength

Thickness mm	Uniform Elongation & Total Elongation (%)																														
	20	21	22	23	24	25	26	27	28	29	30	31	32	33	34	35	36	37	38	39	40	41	42	43	44	45	46	47	48	49	
0.50 - 0.79																															
0.80 - 1.20																															
1.21 - 3.20																															

**Key**  uniform elongation  total elongation

Thickness mm	r-value													
	1.3	1.4	1.5	1.6	1.7	1.8	1.9	2.0	2.1	2.2	2.3	2.4	2.5	2.6
0.50 - 0.79														
0.80 - 1.20														
1.21 - 3.20														

Note: Typical properties from 80mm gauge length test piece in the transverse direction.

BlueScope is a trade mark of BlueScope Steel Limited.

Please ensure you have the current data sheet for this product as displayed at [www.bluescopesteel.com.au](http://www.bluescopesteel.com.au)

### BlueScope Steel Limited

BlueScope Steel Limited ABN 16 000 011 058  
BlueScope Steel (AIS) Pty Ltd ABN 19 000 019 625

Copyright © 2003 BlueScope Steel Limited

**SYDNEY:** (02) 9795 6700 **MELBOURNE:** (03) 9586 2222 **BRISBANE:** (07) 3845 9300 **ADELAIDE:** (08) 8243 7333 **PERTH:** (09) 9330 0666

Produced by Artimprint (02) 9984 8586

