

## ROOF PENETRATIONS

### TECHNICAL BULLETIN CTB-10

Rev 3, November 2003

This issue supersedes all previous issues

The reticulation of services throughout a modern building often require certain penetrations to be made through the roof cladding. Where these vents are fabricated from copper or similar incompatible materials, they must be post painted with an appropriate coating system to prevent the migration of copper ions to the roof surface. The deposition of copper ions will lead to accelerated attack of the ZINCALUME® zinc/aluminium alloy-coated steel and COLORBOND® prepainted steel roof sheeting.

Today the majority of roof penetrations are effectively sealed with a flexible EPDM or silicone rubber flanged sleeve, which can be obtained for flashing penetrations up to 600 mm in diameter. The metal flange around the base of the sleeve should be contoured by hand to match the sheeting profile, before it is sealed and fastened to the sheeting. This allows drainage of water run-off down the trays or valleys each side of the penetration. The sleeve tapers up from the flange to a water tight fit around the penetration. While using these rubber sleeves care must be taken not to block any valleys or trays which would prevent water draining from the high side of the roof penetration. Ponding in such areas will cause deterioration of the sheet coating which will lead to perforation.

However, if the roof penetration can be located closer to the ridge capping or other flashing units, an alternative flashing method would be to fit a simple flat tray water shed, over the top of the sheeting profile.

This should extend from under the flashing or capping down to the sleeve around the penetration thus preventing the ponding of run-off water. Often specialist flashing is required around roof penetrations such as chimneys, skylights and other architectural features. On low pitched roofs any penetration through sheeting large enough to block one or more of the sheet drainage channels or deck pans will require special attention to the flashing around the penetration. This can be achieved by diverting run-off water from the blocked channels by fitting a head gutter on the high side of the penetration. Run-off water from the roof area immediately above the blocked channels is then discharged into clear channels either side of the penetration. It should be noted that the sheeting on the high side has to be stopped clear of the penetration to allow a suitable space for installation of a head gutter which can be flashed under and sealed, to the upper sheet.

Further details pertaining to appropriate flashing methods at roof penetrations are covered in Australian Standard SAA HB39 1997.

The information and advice contained in this Bulletin is of a general nature only, and has not been prepared with your specific needs in mind. You should always obtain specialist advice to ensure that the materials, approach and techniques referred to in this Bulletin meet your specific requirements.

BlueScope Steel Limited makes no warranty as to the accuracy, completeness or reliability of any estimates, opinions or other information contained in this Bulletin, and to the maximum extent permitted by law, BlueScope Steel Limited disclaims all liability and responsibility for any loss or damage, direct or indirect, which may be suffered by any person acting in reliance on anything contained in or omitted from this document.

ZINCALUME® and COLORBOND® are registered trade marks of BlueScope Steel Limited. BlueScope is a trade mark of BlueScope Steel Limited.

*Please ensure you have the current Technical Bulletin as displayed at [www.bluescopesteel.com.au](http://www.bluescopesteel.com.au)*

#### BlueScope Steel

Copyright© 2003 BlueScope Steel Limited

BlueScope Steel Limited ABN 16 000 011 058  
BlueScope Steel (AIS) Pty Ltd ABN 19 000 019 625



AUSTRALIA	SYDNEY	Telephone: (02) 9795 6700
	MELBOURNE	Telephone: (03) 9586 2222
	BRISBANE	Telephone: (07) 3845 9300
	ADELAIDE	Telephone: (08) 8243 7333
	PERTH	Telephone: (08) 9330 0666

OVERSEAS	BlueScope Steel (Malaysia) Sdn Bhd	Telephone: (603) 3250 8333
	BlueScope Steel (Thailand) Limited	Telephone: (66 38) 685 710
	PT BlueScope Steel Indonesia	Telephone: (62 21) 570 7564
	BlueScope Steel Southern Africa (Pty) Limited	Telephone: (27 21) 555 4265